

CONSTIVAP 2.3

Vapour check, suitable for all fibrous insulation mats and boards



Technical data

	Substance
Fleece	Polypropylene
Membrane	Polyolefin-Film

Attribute	Regulation	Value
Colour		white-transparent
Surface weight	EN 1849-2	65±5 g/m ²
Thickness	EN 1849-2	0,20±0,05 mm
sd-value	EN 1931	2,30±0,25 mm
Fire behaviour		E
Tensile strength MD/CD	EN 12311-2	120 N/5 cm / 85 N/5 cm
Elongation MD/CD	EN 12311-2	80 % / 80 %
Nail tear resistance MD/CD	EN 12310-1	55 N / 60 N
Artificial ageing by long term	EN 1296 / EN 1931	passed
Temperature resistance		-40 °C to +80 °C
Coefficient of thermal conductivity		0,17 W/mK
CE labelling	EN 13984	available

Area of application

For use as vapour check and airtightness membrane in roof, wall, ceiling and floor in accordance with the requirements of DIN 4108-7

Delivery forms:

Roll length	Roll width	Roll surface	Roll weight	UE/Pal.
50 m	1,50 m	75 m ²	6 kg	20

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products.

MOLL

Moll
bauökologische Produkte GmbH
Rheintalstraße 35-43
68723 Schwetzingen
Germany
Fon: +49 (0) 6202-27 82 0
Fax: +49 (0) 6202-27 82 21
eMail: info@moll-group.de

Stand: 26.07.2018

For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.



Call us

Great Britain +44 (0)1228 711511

Ireland +353 46 9432104



Email us

info@ecologicalbuildingsystems.com



Find us

Great Britain Ecological Building Systems UK Ltd.,
Cardewlees, Carlisle, Cumbria, CA5 6LF,
United Kingdom

Ireland Ecological Building Systems Ltd.,
Main Street, Athboy. Co. Meath, C15 Y678,
Republic of Ireland