


Declaration of Performance 0068 – CPR – 037/2014 – DP079EN1643400

1. **Unique identification code of the product-type:** Argacem Ultrafine
2. **Type, batch or serial number or any other element allowing identification of the construction product as required under Article 11(4):**
Product name: Argacem Ultrafine
Production date and batch are printed on the package.
Production plant: Diasen Srl - zona Ind.le Berbentina, 5 – 60041 Sassoferrato (AN).
3. **Intended use or uses of the construction product, in accordance with the applicable harmonized technical specification, as foreseen by the manufacturer:**
Specifications for mortar for masonry - Part 1: Mortar for internal and external plasters in compliance with EN 998-1. Appendix ZA. used in finishes for walls, columns, partitions and ceilings.
4. **Name, registered trade name or registered trade mark and contact address of the manufacturer as required under Article 11 (5):** Diasen Srl - zona Ind.le Berbentina, 5 - 60041 Sassoferrato (AN) – www.diasen.com
5. **Where applicable, name and contact address of the authorised representative whose mandate covers the tasks specified in Article (2):**
Not applicable.
6. **System or systems of assessment and verification of constancy of performance of the construction product as set out in Annex V:** System 4.
7. **In case of the declaration of performance concerning a construction product covered by a harmonized standard:**
Diasen Srl - zona Ind.le Berbentina, 5 - 60041 Sassoferrato (AN) – www.diasen.com
Has done
 1. determination of the product-type on the basis of testing, calculation, tabulated values or descriptive documentation of the product;
 2. control of factory production according to system 4.
8. **Declared performance:**

Essential Characteristics	Performance	Test method
Bulk density	950 ± 150 kg/m ²	EN 1015-10
Compressive strength	≥ 4.50 N/mm ² (category CS III)	EN 1015-11
Fire reaction	class A1	EN 13501-1
Adhesion	≥ 0.50 N/mm ² – FP:B	EN 1015-12
Capillary water absorption	≤ 1.90 kg/m ² min ^{0.5} (category W0)	EN 1015-18
Vapour permeability coefficient	μ=8	EN 1015-19
Thermal conductivity λ _{10,dry}	NPD	EN 1745
Durability	Evaluation based on valid arrangements where the mortar is supposed to be used.	
Dangerous substances	See SDS	Regulation EC n. 1272/2008

9. **The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.**
Signed for and on behalf of: Diego Mingarelli – Legal representative
Sassoferrato, 27/10/2016
R04_7.2QEMS rev 0 of 30/06/2013

DiaSen srl
Z. Ind.le Berbentina, 5
60041 Sassoferrato (AN)
P. IVA/C.F. 01553210426





Zona Industriale Berbentina, 5 – 60041 Sassoferrato (AN) –
Italy
www.diasen.com

14
CPR – 037/2014
UNI EN 998-1

ARGACEM ULTRAFINE

*Specifications for mortar for masonry - Part 1: Mortar for internal and external
plasters.*

Bulk density :	950 ± 150 kg/m ²
Compressive strength:	≥ 4.50 N/mm ² (category CS III)
Fire resistance:	class A1
Adhesion:	> 0.50 N/mm ²
Capillary water absorption:	≤ 1.90 kg/m ² min ^{0.5} (category W0)
Vapour permeability coefficient:	μ=8
Thermal conductivity λ _{10,dry} :	NPD
Durability (freeze/thaw cycles):	evaluation based on the valid arrangement where the mortar is supposed to be used.
Dangerous substances :	see SDS.