

Approval body for construction products
and types of construction

Bautechnisches Prüfamt

An institution established by the Federal and
Laender Governments



European Technical Assessment

ETA-05/0037
of 24 August 2023

English translation prepared by DIBt - Original version in German language

General Part

Technical Assessment Body issuing the
European Technical Assessment:

Deutsches Institut für Bautechnik

Trade name of the construction product

"THERMO HANF PREMIUM", "THERMO HANF
PREMIUM PLUS" and "THERMO HANF COMBI JUTE"

Product family
to which the construction product belongs

Insulating material made of hemp or hemp and jute fibres
and binding fibres of PET- or PLA-basic

Manufacturer

HempFlax Building Solutions GmbH
Industriestraße 2
86720 Nördlingen
DEUTSCHLAND

Manufacturing plant

HempFlax Building Solutions GmbH
Industriestraße 2
86720 Nördlingen
GERMANY

This European Technical Assessment
contains

7 pages including 1 annex which form an integral part of
this assessment

This European Technical Assessment is
issued in accordance with Regulation (EU)
No 305/2011, on the basis of

040005-00-1201

This version replaces

ETA-05/0037 issued on 29 October 2021

The European Technical Assessment is issued by the Technical Assessment Body in its official language. Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and shall be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full. However, partial reproduction may only be made with the written consent of the issuing Technical Assessment Body. Any partial reproduction shall be identified as such.

This European Technical Assessment may be withdrawn by the issuing Technical Assessment Body, in particular pursuant to information by the Commission in accordance with Article 25(3) of Regulation (EU) No 305/2011.

Specific Part

1 Technical description of the product

This European Technical Assessment applies to the insulation materials with the designations: "THERMO HANF PREMIUM" and "THERMO HANF PREMIUM PLUS" made of hemp fibres as well as "THERMO HANF COMBI JUTE" made of hemp and jute fibres.

Further trade names for the mentioned designations are specified in Annex A of the European Technical Assessment.

In the following only the designations "THERMO HANF PREMIUM", "THERMO HANF PREMIUM PLUS" and "THERMO HANF COMBI JUTE" are used to distinguish the insulation materials.

The insulation materials contain polymeric or biopolymeric binding fibres, which are thermally hardened during manufacture.

During the manufacturing process the product is provided with a fire protection equipment.

The insulating material in form of mats is made with the following dimensions:

Nominal thickness: minimum 30 mm to 220 mm maximum

Nominal length: 1200 mm or 2400 mm

Nominal widths: 625 mm or 580 mm

For nominal thicknesses of 30 mm to 80 mm the insulating material is also made in form of rolls.

The insulating material is not coated.

The European Technical Assessment has been issued for the products on the basis of agreed data/information, deposited with Deutsches Institut für Bautechnik, which identifies the product that has been assessed. The European Technical Assessment applies only to products corresponding to this agreed data/information.

2 Specification of the intended use in accordance with the applicable European Assessment Document (EAD)

The insulation materials not exposed to compression loads can be used as follows:

- cavity insulation of external and internal walls of timber frame constructions and similar structures
- internal insulation of external walls between supporting construction
- insulation between rafters and timber beams as well as in cavities of corresponding structures
- insulation on topmost storey ceilings which are not subjected to foot traffic, however, are accessible
- internal insulation of ceiling or roof, e.g. insulation beneath the loadbearing construction (e.g. rafters), suspended ceiling
- cavity insulation between flooring joist battens and similar substructures.

The performance according to section 3 only applies if the insulation materials are installed according to the manufacturer's installation instructions and if they are protected from precipitation, wetting or weathering in built-in state and during transport, storage and installation.

Concerning the application of the insulation materials also the respective national regulations shall be observed.

The design value of the thermal conductivity shall be laid down according to relevant national provisions.

3 Performance of the product and references to the methods used for its assessment

For sampling, conditioning and testing the provisions of the EAD No 040005-00-1201 "Factory-made thermal and/or acoustic insulation products made of vegetable or animal fibres" apply.

3.1 Safety in case of fire (BWR 2)

Essential characteristic	Performance
Reaction to fire test acc. to EN ISO 11925-2:2020	Class E acc. to EN 13501-1: 2018

3.2 Hygiene, health and the environment (BWR 3)

Essential characteristic	Performance
Resistance to the growth of mould test acc. to EAD "Factory-made thermal and/or acoustic insulation products made of vegetable or animal fibres", annex B	Evaluation level 0 acc. to EN ISO 846:1997

3.3 Energy economy and heat retention (BWR 6)

Essential characteristic	Performance
Thermal conductivity at a reference temperature of 10 °C test acc. to EN 12667:2001	Declared values for a moisture content of the insulation material at 23 °C and 50 % relative humidity: ¹
"THERMO HANF PREMIUM"	$\lambda_{D(23,50)} = 0,041 \text{ W/(m} \cdot \text{K)}$
"THERMO HANF PREMIUM PLUS"	$\lambda_{D(23,50)} = 0,043 \text{ W/(m} \cdot \text{K)}$
"THERMO HANF COMBI JUTE"	$\lambda_{D(23,50)} = 0,040 \text{ W/(m} \cdot \text{K)}$

¹ The declared value is representative for at least 90 % of the production with a confidence level of 90 % and applies to the density range mentioned in section 3.3.

Essential characteristic	Performance
<p>Conversion of humidity test acc. to EN ISO 10456:2007+AC:2009 the mass-related moisture content at 23 °C/50 % rel. humidity:</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p> <p>the mass-related moisture content at 23 °C/80 % rel. humidity:</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p> <p>the mass-related moisture conversion coefficient (dry to 23 °C/50 % rel. humidity):</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p> <p>the mass-related moisture conversion coefficient (23 °C/50 % rel. humidity to 23 °C/80 % rel. humidity):</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p> <p>moisture conversion factor (dry to 23 °C/ 50 % rel. humidity):</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p> <p>moisture conversion factor (23 °C/ 50 % rel. humidity to 23 °C/ 80 % rel. humidity):</p> <p>"THERMO HANF PREMIUM"</p> <p>"THERMO HANF PREMIUM PLUS"</p> <p>"THERMO HANF COMBI JUTE"</p>	<p>$U_{23,50} = 0,07$ kg/kg</p> <p>$U_{23,50} = 0,08$ kg/kg</p> <p>$U_{23,50} = 0,08$ kg/kg</p> <p>$U_{23,80} = 0,15$ kg/kg</p> <p>$U_{23,80} = 0,17$ kg/kg</p> <p>$U_{23,80} = 0,19$ kg/kg</p> <p>$f_{u1} = 0,07$</p> <p>$f_{u1} = 0,13$</p> <p>$f_{u1} = 0,11$</p> <p>$f_{u2} = 0,24$</p> <p>$f_{u2} = 0,34$</p> <p>$f_{u2} = 0,05$</p> <p>$F_{m1} = 1,01$</p> <p>$F_{m1} = 1,01$</p> <p>$F_{m1} = 1,01$</p> <p>$F_{m2} = 1,02$</p> <p>$F_{m2} = 1,03$</p> <p>$F_{m2} = 1,01$</p>
Water vapour diffusion resistance coefficient	$\mu = 1$ to 2^2
<p>Dimensional deviations:</p> <p>Length and widths: test acc. to EN 822:2013</p> <p>Thickness: test acc. to EN 823:2013</p>	<p>length: ± 2 %</p> <p>width: $\pm 1,5$ %</p> <p>-4 mm / +10 mm or + 10 % ³</p> <p>Relates to class T3 acc. to EN 13171:2012</p>

² The most unfavorable value for the construction shall be applied each.

³ Whichever gives the smallest numerical tolerance.

Essential characteristic	Performance
Squareness: test acc. to EN 824:2013	$S_b \leq 5 \text{ mm/m}$
Flatness: test acc. to EN 825:2013	$S_{\max} \leq 6 \text{ mm}$
Density: test acc. to EN 1602:2013 "THERMO HANF PREMIUM" "THERMO HANF PREMIUM PLUS" "THERMO HANF COMBI JUTE"	35 – 48 kg/m ³ 35 – 48 kg/m ³ 39 – 45 kg/m ³
Dimensionsstabilität bei definierten Temperatur- und Feuchtebedingungen: test acc. to EN 1604:2013 (48 h, 70 °C) "THERMO HANF PREMIUM PLUS" Deviation from length and width: Deviation from thickness: "THERMO HANF PREMIUM" "THERMO HANF COMBI JUTE"	DS(70,-)3 acc. EN 13171:2012 max. $\pm 3 \%$ max. $\pm 3 \%$ No performance assessed No performance assessed
Tensile strength parallel to faces: test acc. to EN 1608:2013	$\geq 30 \text{ kPa}$

4 Assessment and verification of constancy of performance (AVCP) system applied, with reference to its legal base

In accordance with EAD 040005-00-1201, the applicable European legal act is: 1999/91/EC.
The system to be applied is: 3

5 Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited with Deutsches Institut für Bautechnik.

Issued in Berlin on 24. August 2023 by Deutsches Institut für Bautechnik

Frank Iffländer
Head of Section

beglaubigt:
Meyer

"THERMO HANF PREMIUM", "THERMO HANF PREMIUM PLUS" and "THERMO HANF COMBI JUTE"

ANNEX A

Further trade names for "THERMO HANF PREMIUM":

" THERMO CHANVRE PREMIUM", "THERMO HEMP PREMIUM", "THERMO HANF FLEX"
and "stroba HANF PREMIUM "

Further trade names for "THERMO HANF PREMIUM PLUS":

" THERMO CHANVRE PREMIUM PLUS", "THERMO HEMP PREMIUM PLUS", "THERMO HANF FLEX PLUS", "stroba HANF PREMIUM PLUS", "FIBRE NATURELLE ISOLATION", "NATURAL FIBRE INSULATION" and "NATURAHANF FLEX PRO"

Further trade names for "THERMO HANF COMBI JUTE":

"THERMO CHANVRE COMBI JUTE", "THERMO HEMP COMBI JUTE", "stroba HANF COMBI JUTE", "Hanf Jute Dämmung" and "NATURAHANF FLEX"

For over 20 years, Ecological Building Systems has been at the forefront of environmental and sustainable building products supplying a range of innovative airtightness solutions and natural insulations backed up with expert technical support.

As product suppliers in the UK and Ireland, we're happy to assist you with your projects and have expert technical and sales advice on hand.



Call us

Great Britain +44 (0)1228 711511

Ireland +353 46 9432104



Email us

info@ecologicalbuildingsystems.com



Find us

Great Britain Ecological Building Systems UK Ltd.,
Cardewlees, Carlisle, Cumbria, CA5 6LF,
United Kingdom

Ireland Ecological Building Systems Ltd.,
Main Street, Athboy. Co. Meath, C15 Y678,
Republic of Ireland